

Very low viscosity formulation for enhancing color intensity & gloss of natural stones in stone processing industries especially Granites.

SG34, due to its low viscosity, can penetrate deep into the stone providing high color enhancement & gloss. The penetration of RachTR SG34 in dense natural stone is higher than RachTR SG33.

PRODUCT BENEFITS

- Color Enhancement
- Gloss
- Deep Penetration
- High Color Fastness

Coverage

500- 550 Sq. ft. per kg depending on the porosity of the surface

RECOMMENDED SURFACES

- Granite

MIXING RATIO

Part A - Resin - 100 pbw
Part B - Hardener - 33 pbw

SHELF LIFE 1 Year

TECHNICAL DATA

• Form	Liquid
• Pot Life (25° C)	NA
• Drying Time (25° C)	4 Hours
• Viscosity (25° C)	5 to 10 cps

INSTRUCTIONS

DIRECTIONS

Read entire label before using. Use only as directed. Always test on a small area with a 24 hours curing to check desired results. Make sure surface is clean and free of waxes, dirt and coatings. SG 34 should not be applied to wet surfaces. Ensure proper and thorough mixing of resin and hardener.

METHOD OF APPLICATION

1. The slabs which come out of the gang saw should be properly washed. The surface of the slab is to be hand grinded in some cases to make it even and uniform. All loose particles and dust generated during grinding should be cleaned.
2. Weigh the required amount of Part A and Part B in a container.
3. Mix part A and B homogeneously and apply it on the substrate with sponge roller.
4. The coating of SG34 applied on the substrate is allowed to dry. After complete drying the slabs are polished in polishing machine.

5. The drying time will increase if the temperature is low.

6. Clean tools with appropriate solvent immediately after application and allow them to dry in a well-ventilated area.

7. Proper personal protective equipment like gloves, mask and goggles should be worn during application.

STORAGE & HANDLING

1. May be harmful if swallowed.
2. May cause skin, eye & respiratory irritation.
3. Use in a well ventilated area.
4. Do not ingest.
5. Do not freeze or store above 40° C.
6. Do not mix with other chemicals.



The above information is based on the latest stage of our development and application technology. Due to multiplicity of influencing factors, this information must be considered as non-binding. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.