

High performance cementitious adhesive for fixing ceramic tiles and natural stones designed for interior and exterior application.



- EN12004:2017 C2T
- IS 15477:2019 Type 2T



**GreenPro
Certified**

PRODUCT BENEFITS

- Designed for interior and exterior applications
- High tensile strength
- Absorbs high loads
- Slip resistance
- High tensile strength
- Sustains heat aging
- Good underwater shear bond
- Shock resistant
- Zero VOC content

APPLICATION AREAS

- Floors
- Walls
- Showers
- Damp Areas
- Tile on tile applications
- Dry areas
- Worktops

PACKAGING SIZE

20 KG

USAGE

Materials

- Marbles
- Ceramic tile
- Vitrified / Vitreous, Semi-vitreous tile
- Ceramic mosaic tiles
- Terracotta
- Precast terrazzo
- Natural stones

Substrates

- Concrete
- Concrete Masonry
- Cement Mortar Beds
- Cement Plaster
- Ceramic Tile
- Brick Masonry
- Cement Terrazzo
- Existing Natural Stones

* Surface to be cleaned and roughened before installation of Tiles & Stones

COVERAGE

Approximately 70 - 75 sqft per 20 kg bag @3mm thickness

Coverage will vary depending on type and size of tile and substrate smoothness and evenness.

TECHNICAL DATA

• Form	Powder
• Color	White and Grey
• Mixing Ratio	100:28 pbw
• Pot Life	3 hours
• Shelf Life	1 year
• Open Time	> 20 mins
• Time to traffic	24 hours
• Temperature Resistance	-30°C to 150°C

Properties tested to IS15477:2019

Tensile Adhesion Strength (as per Annex A , Clause 5.1)	Desired Values	Actual Values
• Dry Condition	> 1.0 N/mm ²	> 1.42 N/mm ²
• Wet Condition	> 1.0 N/mm ²	> 1.08 N/mm ²
Shear Adhesion Strength (as per Annex B , Clause 5.2)		
• Dry Condition	> 1.25 N/mm ²	> 1.29 N/mm ²
• Heat Ageing Condition	> 1.0 N/mm ²	> 1.28 N/mm ²
• Wet Condition	> 1.0 N/mm ²	> 1.18 N/mm ²
Slip Resistance as per Annex E, Clause 5.5	< 0.5 mm	0.21 mm

Tensile Adhesion Strength (as per EN 1348)	Desired Values	Actual Values
• 28 days in Normal Conditions	≥ 1.0 N/mm ²	> 1.42 N/mm ²
• Thermal Ageing at 70° C for 14 days	≥ 1.0 N/mm ²	> 1.12 N/mm ²
• Freeze - thaw cycles	≥ 1.0 N/mm ²	> 1.04 N/mm ²
Open time @ 20 mins: Tensile Adhesion Strength (EN 1346)	≥ 0.5 N/mm ²	≥ 0.5 N/mm ²
Slip Resistance (as per EN 1308)	≤ 0.5 mm	≤ 0.5 mm

INSTRUCTIONS

SURFACE PREPARATION

- Surface temperature should be between 4° C to 40° C and structurally sound, clean and free of waxes, dirt and coatings, laitance, sealers or curing compounds.
- Dry, dusty concrete slabs or masonry should be cleaned with water and excess water swept off.

APPLICATION METHOD

- Apply adhesive to the substrate with flat side of the trowel, pressing firmly into substrate.
- Comb on additional adhesive with the notched side.
- Use the proper sized notched trowel to ensure full bedding of the tile.
- Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to imbed tile and adjust level.
- Check adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile.
- If adhesive is skinned over (not sticky), remove and replace with fresh adhesive.
- Grouting:- Grout installation should be done after a minimum of 24 hours curing time at 21° C
- During cold weather, protect finished work from traffic until fully cured.

PREPARING THE MIX

- Fill clean, potable water into a container.
- Add RachTR TSA ECO+ powder into the mixing bowl. Use approximately 5-7 L of water for 20 kg of powder
- Ensure proper and thorough mixing with slow speed mixer up till trowelable consistency.
- Adjust consistency if necessary.
- Apply with notch trowel.
- Use Gloves, Goggles and Respirators while applying

EMERGENCY/FIRST AID

- Ingestion: Do not induce vomiting. Call a physician
- Eye Contact: Flush thoroughly with water for at least 15 minutes. Remove contact lenses, if applicable, and continue flushing. Call a physician if eye irritation persists.
- Skin Contact: Wash skin with mild soap and water. Call a physician if skin irritation persists. Wash clothes before wearing again.
- Inhalation: Remove to fresh air. Call a physician if respiratory irritation persists.

STORAGE AND HANDLING

May be harmful if swallowed. May cause skin, eye and respiratory irritation. Do not inhale. Avoid prolonged exposure to powder. Use in a well ventilated area. Do not ingest. KEEP OUT OF THE REACH OF THE CHILDREN. Do not freeze or store above 40° C. Do not mix with other chemicals



The above information is based on the latest stage of our development and application technology. Due to multiplicity of influencing factors, this information must be considered as non-binding. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.