

It is a Liquid, Low viscous, Transparent and Non Yellowing, 2 component Epoxy based filling for white and light colored marbles such as Thassos, Cararra, Statuario, Onyx, etc.



PRODUCT BENEFITS

- Non Yellowing thermosetting
- Solvent Free
- Excellent to fill cracks, pinholes on light colored marbles
- Resistant to Chemicals

USAGE

Materials

- White and Light colored Marbles like Thassos, Statuario, Palisandro, Onyx, Cararra etc.
- Natural stones

PACKAGING SIZE

Part A - 1 Kg
Part B - 0.5 Kg

COVERAGE

Approximately 100-250 sqft per kg

TECHNICAL DATA

• Form	Liquid
• Colors	Transparent
• Specific Gravity Part A (Resin)	1.1
• Specific Gravity Part B (Hardener)	0.94
• Mixing Ratio	2 (Resin) : 1 (Hardener) pbw
• Shelf Life	2 years

• Pot Life	30 minutes
• Curing Time - Touch Dry (25 - 50 deg C)	2 - 3 hours
• Curing Time - Touch Dry (15 - 25 deg C)	5 - 7 hours
• Curing Time - Touch Dry (5 - 15 deg C)	8 - 24 hours
• Full Cure	7 days

INSTRUCTIONS

SURFACE PREPARATION

- Substrate must be thoroughly cleaned and should be free of moisture, dirt, oil and grease
- 201L should not be applied to wet surfaces

PREPARING THE MIX

- Mix Part A and B homogeneously in the ratio of 2 : 1 and applied on the substrate
- Do not mix any other solvents
- The hardener portion should not be more or less than 50 % in the mix otherwise it will reduce adhesion, deteriorate surface drying or delay hardening

APPLICATION METHOD

- Clean surface as mentioned above. Use Gloves during application. Follow manufacturer's instructions of for using gloves.
- Mask any surface not intended to be treated.
- A layer of 201L should be applied on after applying initial grit (cutting) the substrate.
- If excess epoxy is not wiped off, residue appears, mechanically remove the cured epoxy.
- A full cure of a single coat is achieved after 24 hours; foot traffic may begin after 6-8 hours.
- Clean tools with appropriate solvent immediately after application and allow them dry in a well ventilated area
- After 12-20 hours, the treated part can be further processed and transported.

- The low temperatures can significantly affect the curing process.
- The pot life of the product is 30 minutes approximately. So, after mixing use the product within 30 minutes.

EMERGENCY/FIRST AID

- Ingestion: Do not induce vomiting. Call a physician
- Eye Contact: Flush thoroughly with water for at least 15 minutes. Remove contact lenses, if applicable, and continue flushing. Call a physician if eye irritation persists.
- Skin Contact: Wash skin with mild soap and water. Call a physician if skin irritation persists. Wash clothes before wearing again.
- Inhalation: Remove to fresh air. Call a physician if respiratory irritation persists.

STORAGE AND HANDLING

May be harmful if swallowed. May cause skin, eye and respiratory irritation. Do not inhale.

Avoid prolonged exposure to powder. Use in a well ventilated area. Do not ingest.

KEEP OUT OF THE REACH OF THE CHILDREN.

Do not freeze or store above 40° C. Do not mix with other chemicals



RachTR Chemicals Pvt.. Ltd

D-10, 2nd Floor, DDA LSC Naraina, New Delhi -110028

Tel. 011-40793258, 011-40392557

Website: www.rachtr.com - Email: info@rachtr.com

Manufactured in INDIA

The above information is based on the latest stage of our development and application technology. Due to multiplicity of influencing factors, this information must be considered as non-binding. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.